



DRIVING SURFACE PERFECTION™

Version: 1.1

# RAPTOR WHITE



## TECHNICAL DATA SHEET & PROCESS GUIDE

### TOUGH PROTECTIVE COATING

U-POL's RAPTOR Tough and Tintable Protective Coating is a 2K polyurethane coating that provides surfaces with a protective barrier.

### FEATURES

- **DURABLE**  
Provides tough mechanical damage and stain resistant surface.  
Protects against rust and corrosion.
- **U.V. RESISTANT**  
Delivers a high level of fade resistance.
- **WATER RESISTANT**  
Provides a water resistant finish, keeping moisture out and reducing rust.
- **RESISTANT**  
Resistant against fuels, hydraulic oils, animal urine, salt water and more.
- **QUICK & EASY TO USE**  
Easy as Fill-Shake-Shoot.  
Provides excellent adhesion across many substrates.  
Can be applied with Schutz gun, HVLP gun, roller or brush.

### CERTIFICATES

- **FIRE RESISTANCE**  
RAPTOR has passed flammability testing for motor vehicles according to the test methods FMVSS 302, ISO 3795 & BS AU 169A.
- **SLIP RESISTANCE**  
When used with RAPTOR TRACTION Slip Resistant Additive it produces a finish meeting ASTM E303-93.

### SUBSTRATES AND PREPARATION

#### Substrates

- |                  |                     |             |
|------------------|---------------------|-------------|
| • Original Paint | • Polyester Fillers | • SMC       |
| • Aluminium*     | • Most Plastics*    | • E-coat*   |
| • Bare Metal*    | • Fiberglass        | • Concrete* |
| • Galvanized*    | • GRP               | • Wood*     |
- \* Some substrates require additional surface preparation before applying RAPTOR. See Substrate Preparation section for details.



# RAPTOR WHITE



DRIVING SURFACE PERFECTION™

Version: 1.1

## TECHNICAL DATA SHEET & PROCESS GUIDE

### TOUGH PROTECTIVE COATING



#### Substrate Preparation

To achieve best results with RAPTOR, good preparation is essential.

1. Remove all loose material and any rust from the surface to be coated.
2. Clean and degrease the surface.
3. Abrade the surface with P80 -P180 grit sand paper.
4. Re-clean the surface.
  - \* Aluminium, bare metal, and galvanized:  
Localized rub-thrus: prime with an etch primer, such as two coats of RAPTOR Acid Etch Primer.  
Large exposed areas of bare metal: Full 2K primer system required for optimum adhesion and corrosion resistance.
  - \* Rigid Plastic: after abrading, clean and degrease then use an adhesion promoter, such as RAPTOR Adhesion Promoter or SYSTEM S2003.
  - \* Wood: RAPTOR can go direct to stable wood.
  - \* Concrete: for best results, clean the surface and remove dust. Seal first with proprietary concrete sealer before applying RAPTOR.
  - \* OEM E-Coat: scuff the surface with a coarse abrasive pad then clean and degrease.
5. For hard to reach areas such as internal corners etc. coat first with a suitable adhesion promoter for optimal adhesion.

### MIXING



#### Mixing Ratio

As simple as  
FILL - SHAKE - SHOOT®



	SCHUTZ Gun	HVLP Gravity Gun
<b>RAPTOR : Hardener</b>	3:1	3:1
<b>U-POL SYSTEM 20 Fast Thinners</b>	Ready to use, no thinner needed	Up to 15-20% maximum to reduce the texture. About 25% more coverage*. *Addition of thinner/reducer will affect the product VOC.

Simply FILL the RAPTOR coating bottle with 237ml of hardener, replace cap and SHAKE contents vigorously for at least 2 minutes, add colour and SHAKE contents vigorously for at least 2-minutes. SHOOT.

#### Mixing by weight

Grams	Coating (A)	Hardener (B)
1000g	783g	217g
500g	392g	108g

Pot life of RAPTOR when activated is 60-minutes at 20°C (68°F).

Use of an accelerator is not required.

Only mix one bottle of RAPTOR at a time. Clean gun between mixes.

Do not overtighten cap as this may cause the cap to split.

### 2K ISOCYANATE HARDENER

- Specially designed to provide optimum results independent of climatic conditions and size of repair.
- RAPTOR hardener must not be used on its own, it can only be used with RAPTOR coating.



DRIVING SURFACE PERFECTION™

Version: 1.1

# RAPTOR WHITE



## TECHNICAL DATA SHEET & PROCESS GUIDE

### TOUGH PROTECTIVE COATING



Shelf Life

12 months in unopened containers. Lids must be replaced after every use.

Storage Temperature

+5°C (41°F) - +25°C (77°F)

## APPLICATION

### Standard Schutz Application

1. Remove cap from RAPTOR bottle with the mixed RAPTOR.
2. Attach the RAPTOR bottle to the U-POL SCHUTZ GUN.
3. Adjust the air pressure to 2.75 - 4.10 bar (40-60 PSI).
4. Apply to the prepared surface with an even sweeping motion to obtain the desired texture.
5. If applying additional coats allow to flash off for 60 minutes between coats.

U-POL recommends that you spray a test panel with RAPTOR first to ensure the desired texture is achieved.

### How to achieve common textures with a U-POL Schutz Gun;

1. Standard texture through Schutz Gun:

Ø 4 Bar (60 PSI)

Ø Distance from object 50cm (1.5 foot)

Ø 2 coats with an even sweeping motion



2. Coarse texture through Schutz Gun:

Ø Mix RAPTOR and allow to stand for 10-minutes

Ø 3 Bar (45 PSI)

Ø Distance from object 50cm (1.5 foot)

Ø 2 coats - 1 even sweeping motion, 2nd dropping the coat over the first





## TECHNICAL DATA SHEET & PROCESS GUIDE

### TOUGH PROTECTIVE COATING

#### How to achieve common textures with a HVLP gun;

3. Fine texture through HVLP gravity fed gun, 1.6-2.0mm

- Ø Add 15% reducer
- Ø 2 Bar (29 PSI)
- Ø Distance from object 20cm (>0.5 foot)
- Ø 1st coat even wet coat, second coat reduce pressure and material flow to achieve a fine mist



4. Standard texture through HVLP gravity fed gun, 1.6-2.0mm

- Ø Add 15% reducer
- Ø 2 Bar (29 PSI)
- Ø Distance from object 20cm (>0.5 foot)
- Ø 1st and second coats applied as even wet coats



The above recommendations are based on our experience with RAPTOR and represent only a few examples of the types of textures that can be achieved. It is recommended that a trial application is made to fine tune the finish before applying onto the finished object.

#### Rolling RAPTOR

1. Pour mixed RAPTOR into a suitable paint tray.
2. Cut in all corners and hard to reach areas with a brush.
3. Apply using an open textured roller.
4. Load roller with the product and apply slowly using medium pressure.
5. Rolling on RAPTOR results in a lower build. Additional coats will be necessary. When applying additional coats, observe 60 minute flash off period between coats.

Do not use in extreme cold or hot temperatures.

Ideal application temperature is 20°C (68°F) with humidity of less than 60%.



#### Coats

Build / microns  
As applied using SCHUTZ Gun

U-POL recommends applying 2 medium coats of RAPTOR.

1 Coat: 230µ (9.0 Mils)    2 Coats: 475µ (18.7 Mils)

All measurements are approximate and are dependent on the application method. See document "Indicative Consumption" for a variety of applications available from [www.u-pol.com](http://www.u-pol.com).



#### Flash-off / min @ 20°C (68°F)

Between coats

60 minutes

**IMPORTANT!** Do not place heavy loads on the surface until RAPTOR is fully cured. Please see dry times below.



# RAPTOR WHITE



DRIVING SURFACE PERFECTION™

Version: 1.1

## TECHNICAL DATA SHEET & PROCESS GUIDE

### TOUGH PROTECTIVE COATING



#### Drying Times

Touch Dry @ 20°C (68°F) Less than 1 hour

Through Dry @ 20°C (68°F) 5-7 days

Reducing flash off time, excessive film build and/or reduced temperatures will alter drying time. Do not allow RAPTOR to come in contact with water for at least 72-hrs.

Higher temperatures will result in shorter flash time and colder temperatures will require a longer flash time. Higher film builds will extend the final cure time.

#### Baking

RAPTOR can be baked for 30 minutes @ 60°C (140°F). Baking will speed up the initial cure, but it is still recommended waiting 7 days for regular use.

#### I.R. Cure

I.R. curing is not recommended.



#### Over Painting

RAPTOR can be overpainted with most modern paint systems. When overpainting, prep the surface as follows:

1. Let sprayed RAPTOR dry for 24 hours.
2. Abrade with a fine abrasive pad.
3. Clean and degrease.

#### Adding RAPTOR TRACTION Anti-Slip Additive

See RAPTOR TRACTION Anti-Slip Additive SOP.

## PROPERTIES



#### Data

Flash point -18°C (-0.4°F)

Solid content without thinner Approx. 57 %

Specific weight Approx. 1180g/l (9.85lb/gal US)

#### Chemical Resistance

- Diesel: No effect
- Petrol: Surface softening
- Xylene: Surface softening
- Hydraulic Oil: No effect
- NaOH: No effect
- Bleach: No effect
- Alcohol: No effect
- Horse urine: No effect

Dielectric breakdown 10.3 kV/mm (262 V/Mil) ASTM D 149

Temperature Resistance -18°C to 100°C (-0.4°F to 212°F)



DRIVING SURFACE PERFECTION™

Version: 1.1

# RAPTOR WHITE



## TECHNICAL DATA SHEET & PROCESS GUIDE

### TOUGH PROTECTIVE COATING

### STORAGE & VOC INFORMATION



**Shelf Life**

2 years from date of manufacture in sealed original containers.

**Storage**

Should be stored in cool, dry conditions in the original containers.

**Equipment Cleaning**

Clean spray gun in-between mixes. All equipment should be thoroughly washed with acetone immediately after use.



**VOC Information**

The EU limit for this product (product category: IIB(e) in ready to use form is 840g/litre.

The VOC content of this product in ready to use form is 472g/litre.

Order Code	Description	Case Qty
RLW/S4	RAPTOR White 3.8L Kit	1
RLW/200	RAPTOR White 200L Drum	1
RLTR/SM	RAPTOR TRACTION Anti-Slip Additive 200g Packet	20
GUN/1	U-POL Application Gun	5
GUN/VN	U-POL Vari-Nozzle Application Gun	6
RAP/AL	RAPTOR Adhesion Promoter 450ml Aerosol	6
RAEP/AL	RAPTOR Etch Primer 450ml Aerosol	6
S2003/1	SYSTEM 2003 Plastic Primer 1L	6
S2003/AL	SYSTEM 2003 Plastic Primer 450ml Aerosol	6
ACID/1	ACID#8 Etch Primer 1L	6

**IMPORTANT: FOR PROFESSIONAL USE ONLY. Read full instructions before use.**

This product contains hazardous materials and therefore appropriate personal protective equipment should always be used. Please refer to the label and consult the material safety data sheet for full handling instructions and personal protection information. U-POL disclaims any liability where the user does not wear the recommended personal protective equipment. The above data is for information only and may change without prior notice. It is the Buyers responsibility to ensure the suitability of the products for their own use and check the up-to-datedness of this information. The recommendation of use of our products and application are based on our knowledge and experience. Please refer to the label and consult the material safety data sheet for full handling instructions and personal protection information. These are available via your local stockist or via the U-POL website at WWW.U-POL.COM. U-POL is not responsible for the results obtained by others over whose methods we have no control and thereof U-POL is not liable for consequential or incidental damages including loss of profits.

**U-POL AUSTRALIA PTY Ltd**

PO BOX 375  
Springwood NSW 2777  
WWW.U-POL.COM

Contact Australia

T: +61 2 4731 2655  
F: +61 2 4731 2611  
sales@u-pol.com.au

**U-POL NEW ZEALAND Ltd**

T: +64 27 630 3691  
F: +61 2 4731 2611  
sales@u-pol.com

Technical

T: +44 (0)1933 230 310  
F: +44 (0)1933 425 797  
technicaldepartment@u-pol.com