



DRIVING SURFACE PERFECTION™

DOLMA/2 - DOLMA/C3 DOLPHIN Multi-Advance



DESCRIPTION

A premium, technically advanced putty for fine to deep repairs. It improves productivity through a combination of fast curing and easy sanding, even after 24 hrs. Suitable for multiple substrates, it's easy to spread with superior vertical hold. It delivers an ultra-fine, pinhole resistant finish for consistently high-quality results every time. Approved as part of the Axalta standard repair process. U-POL and DOLPHIN® are registered trademarks of U-POL Ltd, an Axalta Coating Systems company© 2024.

FEATURES

- Fast cure (10-15 mins @20°C)
- Easy to sand, even after 24 hours
- Higher stock removal reduces sanding time
- Multi-functional – superior adhesion to multiple substrates incl. Galv
- Smooth, easy to spread
- Excellent vertical hold
- Low surface tack
- Superior pinhole resistance
- Includes hardener and spreader (under overclosure)
- Available in a 1.5 kg Rimless Tin or 2.6 kg Cartridge

TECHNICAL DATA SHEET


DOLMA/2 - DOLMA/C3

DOLPHIN Multi-Advance

Product preparation - application



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



Bare Steel - cleaned with solvent based degreaser and sanded with P80 grit. Re-clean the abraded substrate before application.


Galvanised Steel - cleaned with solvent based degreaser and sanded with P180 grit. Re-clean the abraded substrate before application.

Aluminium - cleaned with solvent based degreaser and sanded with P180 grit. Re-clean the abraded substrate before application.

Fibre Glass / GRP / SMC - cleaned with solvent based degreaser and sanded with P180 grit. Re-clean the abraded substrate before application.

Old or original paintwork - cleaned with solvent based degreaser and sanded with P180 grit. Re-clean the abraded substrate before application.

Existing bodyfiller - cleaned with solvent based degreaser and sanded with P80-P180 grit. Re-clean the abraded substrate before application.



	10°C	20°C	30°C
Mixing Ratio (BPO Hardener)	3%	2%	1%
Gel Time (minutes)	7 - 8	4 - 6	4 - 5
Time to Sand (minutes)	15	10 - 15	10
Maximum Fill Depth	1 - 7 mm		
Infra Red Bake	50 - 80cm, 80°C, 5 minutes		


Mix thoroughly on an Onion Board mixing palette. Follow mix ratio carefully. Do not under or over catalyse. Apply with a pressing action to reduce air entrapment. Not recommended for applications below 5°C.



Potlife at 20°C: 4 min - 6 min



Apply smooth film immediately after mixing, avoiding air entrapment.



Initial Sanding P80 - P120
Final Sanding P180 - P240

VOC compliant

2004/42/IB/b(250) 100: The EU limit value for this product (product category: b) in ready to use form is maximum 250 g/l of VOC. The VOC content of this product in ready to use form is maximum 100 g/l.

TECHNICAL DATA SHEET

DOLMA/2 - DOLMA/C3

DOLPHIN Multi-Advance

Products

DOLPHIN Multi Advance

Waste treatment Dispose of contents / container to approved disposal companies or municipal collection points. Do not empty into drains.

Remarks

- Do not add more hardener than recommended to avoid bleeding and spot marking.
- Reaction temperature should be at least +5°C.
- Recommended storage temperature at 5°C to 25°C.
- Surplus ready for use material should not be returned to original can.
- Store in a well-ventilated place.
- Application of a solvent based primer is recommended to achieve the perfect surface for the colour of your choice.
- For additional technical assistance, please contact the U-POL Technical Department at upol.technicalsupport@axalta.com

Appearance	Paste
Colour	Pale Green
Density	1.53 - 1.58 g/cm ³
Shelf Life	2 yrs

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

All other products referred to in the refinish build up are from our brand product range. System properties will not be valid when the related material is used in combination with any other materials or additives which are not part of our brand product range, unless explicitly indicated otherwise.

For professional use only! The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.