



DRIVING SURFACE PERFECTION™

# TRIM #11 High Build top Coat



## DESCRIPTION

Restores original OEM appearance to body panels, under hood, chassis and wheels.






## FEATURES

- Suitable for use over existing paint surfaces
- Replicates factory look
- High gloss, satin, matte or metallic finish
- Produces a film thickness similar to spray applied topcoats

# TECHNICAL DATA SHEET

## TRIM #11 High Build top Coat

### Product preparation - application

	It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.	
	Factory primer, lightly sanded. Prepared painted surfaces	
	Ready to use	
	Not applicable	
	1 - 2 coats sprayed 15-25cm away from the object	with intermediate flash-off: 3 min - 5 min at 20°C Handleable: 30 min at 20°C Final airdry time: 1 hr at 20°C depending on film build

VOC compliant

2004/42/IIB/e(840) 715: The EU limit value for this product (product category: e) in ready to use form is maximum 840 g/l of VOC. The VOC content of this product in ready to use form is maximum 715 g/l.


# TECHNICAL DATA SHEET

## TRIM #11 High Build top Coat

### Products

- TRIMGB TRIM #11 High Build Topcoat Aerosol Gloss Black
- TRIMGW TRIM #11 High Build Topcoat Aerosol Gloss White
- TRIMMB TRIM #11 High Build Topcoat Aerosol Matt Black
- TRIMSB TRIM #11 High Build Topcoat Aerosol Satin Black
- TRIMSLW TRIM #11 High Build Topcoat Silver Wheels Aerosol
- TRIMSTW TRIM #11 High Build Topcoat Steel Wheels Aerosol

	25 µm Solids 15 µm Metallics
--	---------------------------------

	After use, hold aerosol can upside down and spray briefly to clean nozzle. If the nozzle becomes blocked, remove from the can and soak in gentle thinners before replacing.
--	--

### Remarks

- Theoretical coverage up to 1.5m<sup>2</sup> per unit, assuming 100% transfer efficiency at the specified film build. Colours can vary.
- Can be overcoated with clearcoat after 30 minutes to enhance gloss and give extra protection, especially recommended for metallics.
- Aerosol cans should be stored for 2 hours at room temperature before use. For long term storage keep in a dry well ventilated area and away from direct sunlight and frost. Recommended storage temperature 5 - 25°C, recommended application temperature 20°C
- Aerosol cans should be stored for 2 hours at room temperature before use. For long term storage keep in a dry well ventilated area and away from direct sunlight and frost. Recommended storage temperature 5 - 25°C, recommended application temperature 20°C

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

All other products referred to in the refinish build up are from our brand product range. System properties will not be valid when the related material is used in combination with any other materials or additives which are not part of our brand product range, unless explicitly indicated otherwise.

For professional use only! The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.