



LIGHTWEIGHT FILLER FOR MEDIUM DEPTH REPAIRS

GOLDLWF/M

Version: 3.0

Date of issue: 13/06/2018 Revision date: 07/01/2020 Supersedes: 14/10/2019



DRIVING SURFACE PERFECTION

TECHNICAL DATASHEET

LITEWEIGHT GOLD FOR MEDIUM REPAIRS is a versatile, lightweight filler ideal for filling and shaping medium depth repairs over small to large surface areas. It provides an ultra smooth texture that's easy to spread and sands to a fine feather edge.

- Pinhole resistant.
- Non-sagging, even on vertical surfaces.
- Quick drying - solvent resistant in 15 minutes.
- Easy to sand, even days or weeks after curing.
- Non-porous formula will not shrink or pull back.

Typical Use

Ideal for filling and shaping medium panel damage.



APPLICATION GUIDE

Tools Required



Onion Board Mixing Palette, U-POL Applicator, SYSTEM 20 Degreasers, MAXIMUM Abrasives, MAXIMUM Premium Masks, MAXIMUM Painters Overalls, GUIDE #7 Guide Coat Aerosol

Surface Preparation



	Degreaser	Abrasion
Bare Steel	S2001 Fast/S2002 Slow Solvent-Based Degreaser	P80
Aluminium	S2001 Fast/S2002 Slow Solvent-Based Degreaser	P180
Galvanised	S2001 Fast/S2002 Slow Solvent-Based Degreaser	P180
Original Paint	S2001 Fast/S2002 Slow Solvent-Based Degreaser	P180
Polyester Body Filler	S2001 Fast/S2002 Slow Solvent-Based Degreaser	P80 - P180
GRP	S2000 Water-Based Degreaser	P180

LIGHTWEIGHT FILLER FOR MEDIUM DEPTH REPAIRS is multifunctional and has superb adhesion to all the substrates above.

For best results, good preparation is essential.

Clean and degrease removing dirt, oil, grease and wax using cleaning solutions such as U-POL's SYSTEM 20 Degreasers.

Abrade with grit paper as stated above for each respective substrate.

Re-clean, dry and degrease the abraded substrate ready for application.

Application



	10°C	20°C	30°C
Mixing ratio (BPO Hardener):	3%	2%	1%
Gel Time:	6 – 7 minutes	4 – 6 minutes	4 – 5 minutes
Sandable after:	20 minutes	15 – 20 minutes	15 minutes

Maximum Fill Depth	3 – 5 mm
Infrared Bake:	50 – 80 cm, 80 °C, 5 minutes

Mix thoroughly on an Onion Board Mixing Palette.

Follow mix ratio carefully. Do not under or over catalyse.

Apply with a pressing action to reduce air entrapment.

Not recommended for applications below 5°C.

Sanding



Initial Sanding	P80 - P120
Final Sanding	P180 - P240

U-POL recommends using GUIDE #7 Guide Coat Aerosol during the sanding process to identify the high and low spots. A U-POL Finishing Filler such as DOLPHIN GLAZE can be used to fill imperfections such as pin holes and scratches prior to painting.

Contact Australia
T: +61 2 4731 2655
F: +61 2 4731 2611
info@u-pol.com.au

U-POL AUSTRALIA PTY LIMITED
Unit A, 16 - 20 Cassola Place Penrith
NSW 2750
www.u-pol.com - Australia

U-POL NEW ZEALAND Ltd
c/o Lindsay & Associates Unit H, 12 Amera Place,
East Tamaki Manukau City 2013
New Zealand - www.u-pol.com

Contact New Zealand:
T: +64 27 630 3691
F: +61 2 4731 2611
info@u-pol.com.nz



LIGHTWEIGHT FILLER FOR MEDIUM DEPTH REPAIRS

GOLDLWF/M



DRIVING SURFACE PERFECTION

Version: 3.0

Date of issue: 13/06/2018 Revision date: 07/01/2020 Supersedes: 14/10/2019

TECHNICAL DATASHEET

Over-Painting



U-POL recommends a *SYSTEM 20 Primer* to achieve the perfect surface for the colour of your choice.

TECHNICAL INFORMATION

Physical properties



Appearance	Paste.
Colour	Gold
Density	1.23 (1.2 – 1.26) g/cm ³
Viscosity, dynamic	90000 (80000 – 100000) cP

VOC Information



The VOC content of this product as received is 189 g/l. The VOC content of this product in ready to use form is 100 g/l.

Shelf Life and Storage



Order Code	Format	Shelf Life	Batch Coding System
GOLDLWF/M	3L Tin	4 years	C

- A Date of manufacture, unique 5-digit batch code and expiry date printed on base of tin.
- B Date of manufacture and/or 5-digit batch code printed on base of tin/adhesive label/adhesive label on kit box. e.g. 93822 = 2019, week 38, batch 22
- C Date of manufacture and unique 5-digit batch code and printed on base of tin/adhesive label.
- D Date of manufacture and unique 5-digit batch code printed on cartridge.
- E Date of manufacture and unique 7-digit code printed on lid.
- F Date of manufacture and unique 6-digit batch number printed on packaging.
- G Date of manufacture and unique 4-digit batch code and printed on base of tin.
- H Date of manufacture and batch number incorporated into 8-digit code e.g. 18071234 = (18) 2018, (07) July, batch number 1234
- I Date of manufacture printed on tin.
- J Date and time of manufacture printed on neck of aerosol.
- K Date of manufacture and weight of sachet embossed on seal. e.g. 40G 110717
- L Unique 5-digit batch code printed on packaging/adhesive label/embossed on seal. For the date of manufacture, please quote this code to technicalsupport@u-pol.com.
- M Unique 5-digit batch number followed by weight printed on tube. e.g. 17149GR78 = batch number 17149GR, weight 78 g. For the date of manufacture, please quote this code to technicalsupport@u-pol.com.
- N Date of filling and unique 7 digit batch code stamped on adhesive label.
- O LOT number ending in a unique 5-digit code printed on sachet. For the date of manufacture, please quote this code to technicalsupport@u-pol.com.
- P Date of aerosol manufacture and 5-digit aerosol base batch code printed on base of tin. e.g. 93822 = 2019, week 38, batch 22
- Q Date of aerosol manufacture and unique 5-8 digit batch code printed on base of tin.

Recommended storage temperature 5 °C - 25 °C

Store in a well-ventilated place. Keep cool. Keep container tightly closed. Store locked up. Keep only in original container.

For any other information please contact technicalsupport@u-pol.com for assistance.

IMPORTANT: FOR PROFESSIONAL USE ONLY. Read full instructions before use.

This product contains hazardous materials and therefore appropriate personal protective equipment should always be used. Please refer to the label and consult the safety data sheet for full handling instructions and personal protection information. U-POL disclaims any liability where the user does not wear the recommended personal protective equipment. The above data is for information only and may change without prior notice. It is the Buyers responsibility to ensure the suitability of the products for their own use and check the information is up to date. The recommendation of use of our products and application in our technical data sheets are based on our knowledge and experience. These data sheets are available via your local stockist or via the U-POL website at WWW.U-POL.COM. U-POL is not responsible for the results obtained by others over whose methods we have no control and thereof U-POL is not liable for consequential or incidental damages including loss of profits.

Contact Australia
T: +61 2 4731 2655
F: +61 2 4731 2611
info@u-pol.com.au

U-POL AUSTRALIA PTY LIMITED
Unit A, 16 - 20 Cassola Place Penrith
NSW 2750
www.u-pol.com - Australia

U-POL NEW ZEALAND Ltd
c/o Lindsay & Associates Unit H, 12 Amera Place,
East Tamaki Manukau City 2013
New Zealand - www.u-pol.com

Contact New Zealand:
T: +64 27 630 3691
F: +61 2 4731 2611
info@u-pol.com.nz