



DRIVING SURFACE PERFECTION

TECHNICAL DATA SHEET

# S2025

2K UHS PRIMER FILLER 4:1 MIX

## TECHNICAL DATA SHEET & PROCESS GUIDE

S2025 is a high solids VOC compliant 2K acrylic coating that can be used as a multi-role coating

- High build primer filler for spot repairs at 4:1
- Primer surfacer for larger areas at 4:1+10% thinner
- Tintable with up to 10% solvent based mixing base

## PROPERTIES

- Excellent opacity and coverage
- Excellent film build surface levelling properties
- Can be air dried, low baked or IR Cured
- Easy to sand with high gloss holdout

**Available Colours** • Grey • Black • White

## TECHNICAL DATA



### Substrates

- Original Paint
- Mild Steel
- E-coat
- etch primer (for galv/ aluminium)
- SMC
- U-POL Polyester Fillers

	Base	Mixed
<b>Viscosity</b>		40 - 65 s/ DIN 4
<b>Solid content</b>	76.50%	68.50%
<b>Specific gravity g/cm<sup>3</sup></b>	1.69	1.55

## APPLICATION GUIDE



### Tools Required

- SYSTEM 20™ Degreaser
- MAXIMUM Abrasives
- HVLP Gravity Gun
- MAXIMUM Painters Overalls

### Hardener Selection

Please note this product is compatible with the S2030 to S2033 range

Temperature °C	Hardener
-5 -15°C	S2031
5 - 25°C	S2030
15 - 35°C	S2032
25 - +40°C	S2033



DRIVING SURFACE PERFECTION  
TECHNICAL DATA SHEET

# S2025

2K UHS PRIMER FILLER 4:1 MIX

## TECHNICAL DATA SHEET & PROCESS GUIDE



### Substrate Preparation

To achieve best results, good preparation is essential. Degrease with U-POL Precleaner (S2000, S2001 or S2002). Abrade the surface:

Original cured paint: wet flat with P320 or dry flat with P280.

Bare Metal (mild steel): abrade with P180.

Aluminium and zinc coated steel: must first be coated with 1-2 light coats of ACID#8 1K Etch Primer and allowed to dry for 20 minutes.

GRP, SMC, Glass fibre, Polyester Filler: dry flat with P240.

Before applying primer, clean lightly once more with SYSTEM 20 Degreasers and dry thoroughly.



### Mixing Ratio

	High Build Primer	Primer Surfacer
<b>S2025:Hardener</b>	4:1	4:1
<b>20:42 Thinners</b>	nil	10%
<b>Mixing by Weight (grams)</b>		
<b>S2025</b>	200	200
<b>S2032</b>	29.2	29.2
<b>2042 Thinners</b>		12.8



### Viscosity DIN 4 / sec

Working Pot-Life @ 20°C	50 - 65	40 - 45
	1 - 2 hours	1 - 2 hours



### Compliant HVLP Gravity Gun

Gun tip size	1.7 - 2.0mm	1.6 - 1.8mm
Air Pressure at the gun	1.8 - 2.0 bar	



### Coats

	1 - 2 coats	2 - 3 coats
Build / microns	approx 180	100 - 120



### Flash-off @ 20°C

Between coats	15 mins	10 mins
---------------	---------	---------



DRIVING SURFACE PERFECTION  
TECHNICAL DATA SHEET

# S2025

2K UHS PRIMER FILLER 4:1 MIX

## TECHNICAL DATA SHEET & PROCESS GUIDE



### Drying Times

Sandable @ 20°C	3 - 4 hours	3 - 4 hours
Sandable @ 60°C	30 mins	30 mins



### Sanding

Dry Sanding / Abrasive	P320 - P400	P500 - P600
Wet Sanding / Abrasive	P320 - P400	P500 - P600



### Over Painting

S2025 Primer formulation can be directly topcoated with most solvent and water-based basecoats or solid colours.

## STORAGE & VOC INFORMATION



### Shelf Life

2 years from date of manufacture in sealed original containers.

**Recommended Storage Temperature** 5°C - 25°C

**Recommended Application Temperature** As per the Hardener Selection table above.

**Equipment Cleaning** Clean gun Immediately after use with SYSTEM 20 thinner or gunwash.

### Important Remarks

Do not use activated product beyond pot life.  
Activated material should not be returned to the original can of non-activated material.  
After 10 minutes standing, the paint may need mild agitation to reliquify before 2nd and 3rd coat applications.



### VOC Information

The EU limit for this product (product category: IIB.(b) in ready to use form is 540 g/litre.  
The VOC content of this product in ready to use form is 495 g/litre.

#### Ready to use VOC g/l

	Colour	High Build Primer	Primer Surfacer
	All colours	453	495



DRIVING SURFACE PERFECTION

TECHNICAL DATA SHEET

# S2025

2K UHS PRIMER FILLER 4:1 MIX

## TECHNICAL DATA SHEET & PROCESS GUIDE

Order Code	Format	Colour
S2025/3T	3L Tin	Grey Primer
S2025/4	4L Tin	Grey Primer
S2025B/1	1L Tin	Black Primer
S2025B/4	4L Tin	Black Primer
S2025W/1	1L Tin	White Primer
S2025W/3T	3L Tin	White Primer
S2025W/4	4L Tin	White Primer

**IMPORTANT: FOR PROFESSIONAL USE ONLY. Read full instructions before use.**

This product contains hazardous materials and therefore appropriate personal protective equipment should always be used. Please refer to the label and consult the safety data sheet for full handling instructions and personal protection information. U-POL disclaims any liability where the user does not wear the recommended personal protective equipment. The above data is for information only and may change without prior notice. It is the Buyers responsibility to ensure the suitability of the products for their own use and check the information is up to date. The recommendation of use of our products and application in our technical data sheets are based on our knowledge and experience. These data sheets are available via your local stockist or via the U-POL website at [WWW.U-POL.COM](http://WWW.U-POL.COM). U-POL is not responsible for the results obtained by others over whose methods we have no control and thereof U-POL is not liable for consequential or incidental damages including loss of profits.

---

**U-POL AUSTRALIA PTY Ltd.**  
Unit A, 16-20 Cassola Place,  
Penrith, NSW 2750.  
Australia

Tel: 02 4731 2655  
Emergency Tel: +61 290 372 994  
Fax: +61 290 372 994

Email: [info@u-pol.com.au](mailto:info@u-pol.com.au)  
Web: [www.u-pol.com.au](http://www.u-pol.com.au)